

DRÄHTE FÜR FUNKENERODIERTECHNIK



spezielle Glühanlagen sichern den hohen Qualitätsstandard

DAG Cut - Messingdraht CuZn 37

Oberfläche	Zugfestigkeit	Durchm. (mm)	Tol (mm)	E-Leitfähigkeit (m/ Ω mm ²)
blank	400	0,15/0.20/0.25/0,30	+0/ -0,002	15,5
blank	500	0,15/0.20/0.25/0,30	+0/ -0,002	15,0
blank	900/950/1000	0,15/0.20/0.25/0,30	+0/ -0,002	13,5

DAG Cut A - Messingdraht CuZn 37

verzinkt	500	0,15/0.20/0.25/0,30	+0/ -0,002	14,5
verzinkt	900/1000	0,15/0.20/0.25/0,30	+0/ -0,002	13,5

DAG Cut X - Kupferdraht

behandelt	500	0.25/0,30	+0/ -0,002	50,0
-----------	-----	-----------	------------	------

Aufmachung

Spulentyp	Füllgewicht pro Spule(kg)	Spulen pro Karton	Nettogew. pro Palette (kg)
DIN 100	2,0	16	512,0
DIN 125	3,5	4	448,0
DIN 160	7,0	2	672,0
DIN 200	16,0	1	720,0
DIN 250	25,0	1	450,0
DIN 355	45,0	1	405,0
P 3	3,0	4	384,0
P 5	5,0	2	480,0
P 10	10,0	2	600,0
P 15	20,0	1	560,0

DUROFER AG

Moosstrasse 20
CH - 9014 St. Gallen - SWITZERLAND

www.durofer.ch
info@durofer.ch

Teil : +41 (0)71 272 23 50
Fax : +41 (0)71 272 23 59

